

<b>MAINTENANCE PLANNING GUIDELINES</b>	2006
--	------

<b>ACTIVITY:</b> Other Pavement Maintenance (R314) <b>MAJOR &amp; MINOR</b>	<b>ACTION:</b> Cold Milling
--	-----------------------------

**DEFINITION:** The time and expenses incurred to maintain pavements not specified elsewhere. Examples include cold-milling and blading aggregate roads. Includes cost of using a mud jack or other equipment to level pavements or fill voids under pavements and bridges approach slabs.

**PURPOSE:** To restore rideability or drainage to asphalt or concrete surfaces.

<b>SCHEDULING:</b> As needed.	<table border="1" style="margin: auto; border-collapse: collapse;"> <tr> <td>J</td><td>F</td><td>M</td><td>A</td><td>M</td><td>J</td><td>J</td><td>A</td><td>S</td><td>O</td><td>N</td><td>D</td> </tr> <tr> <td>A</td><td>E</td><td>A</td><td>P</td><td>A</td><td>U</td><td>U</td><td>U</td><td>E</td><td>C</td><td>O</td><td>E</td> </tr> <tr> <td>N</td><td>B</td><td>R</td><td>R</td><td>Y</td><td>N</td><td>L</td><td>G</td><td>P</td><td>T</td><td>V</td><td>C</td> </tr> </table>	J	F	M	A	M	J	J	A	S	O	N	D	A	E	A	P	A	U	U	U	E	C	O	E	N	B	R	R	Y	N	L	G	P	T	V	C
J	F	M	A	M	J	J	A	S	O	N	D																										
A	E	A	P	A	U	U	U	E	C	O	E																										
N	B	R	R	Y	N	L	G	P	T	V	C																										

<b>RECOMMENDED EQUIPMENT:</b> <ul style="list-style-type: none"> <li>• Cold Mill w/Trailer</li> <li>• Trucks</li> <li>• Loader or Power Broom</li> <li>• Traffic Control Equipment; (See EPG <a href="#">616.23 Traffic Control for Field Operations</a>)</li> </ul>	<b>RECOMMENDED PROCEDURE:</b> <ol style="list-style-type: none"> <li>1. Place traffic control devices as needed.</li> <li>2. Mill affected area to desired template.</li> <li>3. Pick up milled material and clean area.</li> <li>4. Remove traffic control devices.</li> </ol>
--	---

<b>RECOMMENDED MATERIAL:</b> <ul style="list-style-type: none"> <li>• None</li> </ul>	
---	--

**SAFETY:** Keep clear of equipment. Refer to the [Safety Policies, Rules & Regulations – Employee Handbook](#).

**OTHER CONSIDERATIONS:** When milling multipatched asphalt area, a sand or cinder seal will lessen the chance of raveling.

**REFERENCES:** Missouri Standard Specifications for Highway Construction Section; Section [622.10](#).